

銅 | JIS規格と海外規格の比較表

作成期日：2026.07.03

材質種類 (分類)	日本 (JIS)	中国 (GB)	ドイツ (DIN)	アメリカ (AISI)	比重 (kg/mm ³)
無酸素銅	C1020	T1 TU1 TU2	Cu-OF (2.0040)	C10200	8.94
タフピッチ銅	C1100	T2	Cu-ETP (2.0060)	C11000	8.94
すず入り銅	C1441		CuSn0.15 (2.1050)	C14410	8.9
ばね用ベリリウム銅	C1720	QBe2 QBe1.9-0.1	CuBe2 (2.1247)	C17200	8.25
丹銅	C2100	H96	CuZn5 (2.0220)	C21000	8.8
	C2200	H90	CuZn10 (2.0230)	C22000	
	C2300	H85	CuZn15 (2.0240)	C23000	
	C2400	H80	CuZn20 (2.0250)	C24000	
七三黄銅	C2600	H68 H70	CuZn30 (2.0265)	C26000	8.5
	C2680	H65	CuZn33 (2.0270)	C26800	
	C2700	H63	CuZn35 (2.0280)	C27000	
65/35黄銅	C2720	H32	CuZn37 (2.0321)	C27200	8.5
	C2800	H59	CuZn40 (2.0360)	C28000	8.4
快削黄銅	C3560	HPb63-3	CuZn39Pb3 (2.0401)	C36000	8.4
	C3710	HPb62-0.8	CuZn40Pb2 (2.0410)	C37100	
	C3601	HPb62-3	CuZn39Pb3 (2.0402)	C36010	
	C3713	HPb62-2	CuZn40Pb2 (2.0410)	C37130	
	C3710	HPb61-1	CuZn40Pb1 (2.0415)	C37100	
ネーバル黄銅	C4621	HSn62-1	CuZn40Sn1 (2.0460)	C46400	8.5
	C4640	HSn60-1	CuZn40Sn1 (2.0460)	C46400	
りん青銅	C5102	QSn4-0.3	CuSn4 (2.1020)	C51000	8.8
	C5191	QSn6.5-0.4	CuSn6 (2.1030)	C51900	
ばね用りん青銅	C5210	QSn8-0.3	CuSn8 (2.1040)	C52100	8.8
アルミニウム青銅	C6161	QA19-4, QA10-3-1.5	CuAl10Ni5Fe4 (2.0966)	C61600	7.7
	C6280	QA19-5-1-1	CuAl10Ni5Fe4 (2.0966)	C62800	
	C6301	QA10-4-4 QA10-5-5	CuAl10Ni5Fe4 (2.0966)	C63000	
白銅 (キューロニッケル)	C7100	B19	CuNi10Fe1Mn (2.0882)	C71000	8.9
	C7150	B30	CuNi30Mn1Fe (2.0881)	C71500	
	C7060	BFe10-1-1	CuNi10Fe1Mn (2.0882)	C70600	
洋白	C7521	BZn18-18	CuNi18Zn20 (2.0740)	C75200	8.7
	C7701	BZn18-26	CuNi18Zn27 (2.0742)	C77000	
	C7541	BZn15-20	CuNi15Zn20 (2.0741)	C75400	
快削洋白	C7941	BZn15-21-1.8	CuNi15Zn21Pb1.8 (2.0745)	C79400	



監修：PALETTE CO.,LTD