

ステンレス鋼 | JIS規格と海外規格の比較表

作成期日：2026.07.03

材質種類 (分類)	日本 (JIS)	中国 (GB)	ドイツ (DIN)	アメリカ (AISI)	比重 (kg/mm ³)
ステンレス鋼	SUS201	1Cr17Mn6Ni5N	1.4372	201	7.93
	SUS202	1Cr18Mn8Ni5N	1.4373	202	
	SUS301	1Cr18Mn10Ni5Mo3N, 1Cr17Ni7	1.431	301	
	SUS301L		1.4318	301L	
	SUS301J1		1.4319	301J1	
	SUS302	1Cr18Ni9	1.4319	302	
	SUS302B		1.4319	302B	
	SUS303	Y1Cr18Ni9	1.4305	303	
	SUS303Se	Y1Cr18Ni9Se	1.4305	303Se	
	SUS304	0Cr18Ni9	1.4301	304	
	SUS304L	00Cr18Ni10	1.4306	304L	
	SUS304N1	0Cr18Ni9N	1.4315	304N	
	SUS304N2	0Cr19Ni10NbN	1.4316	304N2	
	SUS304LN	00Cr18Ni10N	1.4311	304LN	
	SUS304J1		1.4311	304J1	
	SUS304J2		1.4311	304J2	
	SUS304J3		1.4311	304J3	
	SUS305	1Cr18Ni12	1.4303	305	
	SUS305J1		1.4303	305J1	
	SUS309S	0Cr23Ni13	1.4828	309S	
	SUS310S	0Cr25Ni20	1.4845	310S	
	SUS316	0Cr17Ni12Mo2	1.4401	316	
	SUS316F		1.4401	316F	
	SUS316L	00Cr17Ni14Mo2	1.4404	316L	
	SUS316N	0Cr17Ni12Mo2N	1.4406	316N	
	SUS316LN	00Cr17Ni13Mo2N	1.4429	316LN	
	SUS316Ti		1.4571	316Ti	
	SUS316J1	0Cr18Ni12Mo2Cu2	1.4435	316J1	
	SUS316J1L	00Cr18Ni14Mo2Cu2	1.4436	316J1L	
	SUS317	0Cr19Ni13Mo3	1.4449	317	
	SUS317L	00Cr19Ni13Mo3	1.4438	317L	
	SUS317LN		1.4439	317LN	
	SUS317J1	0Cr18Ni16Mo5	1.4462	317J1	
	SUS317J2		1.4462	317J2	
	SUS836L		1.4539	904L	
	SUS890L		1.4539	904L	
	SUS321	1Cr18Ni9Ti, 0Cr18Ni10Ti	1.4541	321	
	SUS347	0Cr18Ni11Nb	1.455	347	
	SUS384		1.4318	384	
	SUSXM7	0Cr18Ni9Cu3	1.4301	XM7	
	SUSXM15J1	0Cr18Ni13Si4	1.4828	XM15J1	
	SUS329J1	0Cr26Ni5Mo2	1.446	329	
	SUS329J3L		1.4462	2205 (Duplex)	
	SUS329J4L		1.4462	2507 (Super Duplex)	
	SUS405	0Cr13Al, 0Cr13	1.4	405	
SUS410L	00Cr12	1.4003	410L		
SUS429		1.4512	429		
SUS430	1Cr17	1.4016	430		
SUS430F	Y1Cr17	1.4104	430F		
SUS430LX		1.4512	430LX		
SUS430J1L		1.4512	430J1L		
SUS434	1Cr17Mo	1.4113	434		
SUS436L		1.4526	436L		
SUS436J1L		1.4526	436J1L		
SUS444		1.4521	444		
SUS444J1	00Cr30Mo2	1.4529	444J1		
SUSXM27	00Cr27Mo	1.4529	XM27		
SUS403	1Cr12	1.4	403		
SUS410	1Cr13	1.4006	410		
SUS410S		1.4003	410S		
SUS410F2		1.4005	410F2		
SUS410J1	1Cr13Mo, 1Cr12Mo	1.4006	410J1		
SUS416	Y1Cr13	1.4005	416		
					7.98
					7.93
					7.98
					7.75

	SUS420J1	2Cr13	1.4021	420	7.75
	SUS420J2	3Cr13	1.4028	420	
	SUS420F	Y3Cr13	1.4028	420F	
	SUS420F2		1.4028	420F2	
	SUS429J1		1.4512	429	
	SUS431	1Cr17Ni2	1.4057	431	
	SUS440A	7Cr17	1.4108	440A	
	SUS440B	8Cr17	1.4112	440B	
	SUS440C	9Cr18, 11Cr17, 9Cr18Mo	1.4125	440C	
	SUS440F	Y11Cr17	1.4104	440F	
	SUS630	0Cr17Ni4CuNb	1.4542	17-4PH	
	SUS631	0Cr17Ni7Al	1.4568	17-7PH	
	SUS632J1		1.4548	15-5PH	
耐熱鋼	SUH31		1.4841	310	7.93
	SUH35		1.4841	310	
	SUH36	5Cr21Mn9Ni4N	1.4845	310S	
	SUH37	2Cr21Ni12N	1.4845	310S	
	SUH38		1.4845	310S	
	SUH309	2Cr23Ni13	1.4828	309	
	SUH310	2Cr25Ni20	1.4845	310	
	SUH330	1Cr16Ni35	1.4864	330	8.2
	SUH660	0Cr15Ni25Ti2MoAlVB	1.498	Nimonic 80A	
	SUH661		1.498	Nimonic 90	7.93
	SUH21		1.4876	321	
	SUH409		1.4512	409	7.75
	SUH409L		1.4512	409L	
	SUH446	2Cr25N	1.4526	446	
	SUH1	4Cr9Si2	1.4713	405Si	
	SUH3	4Cr10Si2Mo	1.4742	410SiMo	7.93
	SUH4	8Cr20Si2Ni	1.4828	309Si	
	SUH11		1.4841	310	
SUH600	2Cr12MoVNbN	1.4876	600 (Inconel 600)	8.47	
SUH616	2Cr12NiMoWV	1.4886	601 (Inconel 601)		



監修：PALETTE CO.,LTD